


GlasRoc™ Sheathing Exterior Designs Soffits

- ▶ **GlasRoc™ Sheathing** is a superior product for a flat ceiling entryway, exterior ceiling, or a soffit assembly, due to its ability to resist deteriorating effects of moisture and humidity.



09260

Flat Ceiling Entryways, Exterior Ceilings & Soffits

The industry defines the amount of permissible sagging in a horizontal application as humidified deflection. There are several ASTM Standard Specifications that define a maximum allowable humidified deflection including ASTM C 79, ASTM C 931, and ASTM C 1177. Of these, ASTM C 1177 has the most stringent requirements. Note how **GlasRoc™ Sheathing** performs.

Installation Recommendations for Exterior Soffits

Use **GlasRoc™ Sheathing** in exterior soffit systems where weather-resistant performance is critical, including but not limited to, soffits with finished joints and soffits without insulation.

Install the product like a standard gypsum soffit board. Fasten the product to the framing members using the recommendations specified in GA-216 and ASTM C 840.

GlasRoc™ Sheathing in Exterior Ceiling & Soffit Applications

Properties	12.7 mm (1/2") GlasRoc™ Sheathing	12.7 mm (1/2") Gypsum Soffit Board	15.9 mm (5/8") GlasRoc™ Sheathing Type X	15.9 mm (5/8") Gypsum Type X Soffit Board	ASTM TEST METHOD
Surface	Acrylic	Paper	Acrylic	Paper	N/A
Humidified Deflection (Sag)	1.6 mm (1/16")	22 mm (7/8")	0.4 mm (1/64")	13 mm (1/2")	C 473
Water Absorption % by Weight	<10%	40%	<10%	44%	C 473
Surface Water Absorption - grams	<1.6	2.0	<1.6	2.0	C 473

Referenced Standards

- ASTM C 514: Specification for Nails for the Application of Gypsum Board
- ASTM C 931: Standard Specification for Exterior Gypsum Soffit Board
- ASTM C 840: Standard Specification for Application and Finishing of Gypsum Board
- ASTM C 954: Specification for Steel Drill Screws for the Application of Gypsum Panel Products or Metal Plaster Bases to Steel Studs from 0.33 in. (0.84 mm) to 0.112 in. (2.84 mm) in Thickness
- ASTM C 1002: Standard Specification for Steel Drill Screws for the Application of Gypsum Panel Products or Metal Plaster Bases
- ASTM C 1177: Standard Specification for Glass Mat Gypsum Substrate for Use as Sheathing
- ASTM C 1397: Practice for Application of Class PB Exterior Insulation and Finish Systems
- CAN/ULC-S102 / ASTM E 84: Test Method for Surface Burning Characteristics of Building Materials
- ASTM E 96: Test Methods for Water Vapour Transmission of Materials

For more information visit www.glasroc.ca or www.bpb-na.com or call (905) 823-9881.