

CertainTeed

ProRoc[®]
BRAND

Interior Job Condition Specifications for the Application of Drywall Joint Compounds, Drywall Textures, and Paints/Coatings.

Technical Data Sheet

1. SCOPE

All walls, partitions, and ceilings to which drywall joint compounds, drywall textures (where applicable), and paints/ coatings are to be applied are included.

- 1.1 This specification covers the conditioning of gypsum board and concrete prior to the application of drywall joint compounds, drywall textures, and paints/coatings.
- 1.2 This specification covers the interior job conditions during the application of drywall joint compounds, drywall textures, and paints/coatings.
- 1.3 All materials to be used in accordance with all codes, specifications, and manufacturer's recommendations.

2. SUBSTRATE PREPARATION

- 2.1 The gypsum board shall be maintained at a minimum temperature of 13°C (55°F), and be dry for at least 48 hours prior to application of drywall joint compounds, drywall textures, and paints/coatings
- 2.2 Concrete surfaces shall be aged at least 60 days prior to the application of joint compounds, drywall textures, and paints/coatings. All efflorescence, from release agents, dust or other surface contaminants shall be removed.
The concrete surface shall be dry. Exposed metal shall be hand tool cleaned and primed with a rust-inhibitive primer. The concrete surface shall be maintained at a minimum temperature of 13°C (55°F).

3. INTERIOR JOB CONDITIONS

- 3.1 A minimum temperature of 13°C (55°F) shall be maintained continuously for the application of the drywall joint compounds, drywall textures, and paint/coatings until dry.

- 3.2 Continuous ventilation shall be provided to allow proper drying.
- 3.3 Whenever possible permanent heating and ventilation systems should be utilized.
- 3.4 Whenever possible permanent lighting should be utilized.
- 3.4.1 Job site lighting may not be representative of final lighting. Inspection shall take place under job site lighting conditions.
- 3.5 All drywall joint compounds shall be dry or, with setting type drywall joint compounds, hardened (set) prior to the application of subsequent coats.
- 3.6 All drywall joint compounds shall be dry prior to the application of drywall textures and paints/coatings.

4. DRYWALL JOINT COMPOUND, DRYWALL TEXTURE, AND PAINT/COATING APPLICATION

- 4.1 Drywall joint compounds, drywall textures, and paints/ coatings are to be mixed and applied in accordance with the manufacture's recommendations.

5. INTERIOR CONDITIONS FOR FINISHED BUILDINGS.

- 5.1 All finished walls, partitions, and ceilings shall be maintained at a minimum temperature of 13°C (55°F).

Date: 3/20/96

Reprinted by permission of the Drywall Finishing Council Incorporated
(A Non-Profit Mutual Benefit Corporation)

CertainTeed Corporation
P.O. Box 860
Valley Forge, PA 19482

Professional: 800-233-8990
Consumer: 800-782-8777
www.certainteed.com

CertainTeed 

Characteristics, properties or performance of materials or systems manufactured by CertainTeed herein described are derived from data obtained under controlled test conditions. CertainTeed makes no warranties, express or implied, as to their characteristics, properties or performance under any variations from such conditions in actual construction. CertainTeed assumes no responsibility for the effects of structural movement.

™© CertainTeed and the tag line "Quality made certain. Satisfaction guaranteed." are trademarks of CertainTeed Corporation. All other trademarks are the property of its affiliates and related companies.

NOTICE: The information in this document is subject to change without notice. CertainTeed assumes no responsibility for any errors that may inadvertently appear in this document.

©2008 CertainTeed Corporation. Printed in Canada on recycled paper. ♻️ February 2008 Form #: L-TD-003-B